

# TECHNICAL DATA SHEET & PRODUCT SPECIFICATIONS



Issued: June 20<sup>th</sup>, 2023

Product denomination:	Pearlescent Pigment	CLAREIUM 8004
<b>Physical Properties</b>		<b>Test Method</b>
Physical Form:	Dry powder	N/A
Appearance:	Purple Powder	N/A
Particle size Range:	50-250 µm	Laser Diffraction
Density	2.5 – 2.8 g/cm <sup>3</sup>	DIN-ISO-787-10
pH 10% Aqueous Slurry	6-10	DIN-ISO-787-9
Oil Absorption	80-120 g/100 g	GB/T5211.15-88
Chemical Resistance	Stable in Dilute Acid & Alkali	N/A

<b>Composition - International Nomenclature of Cosmetics Ingredients (INCI) :</b>				<b>Nominal</b>	<b>Unit</b>	<b>Test Method</b>
Calcium Aluminum borosilicate	CI: unlisted	CAS: 65997-17-3	EINECS:	80-83	%	ESCA
Titanium dioxide	CI : 77891	CAS: 13463-67-7	EINECS : 236-675-5	16-18	%	ESCA
Tin dioxide	CI : 77861	CAS: 18282-10-5	EINECS : 242-159-0	1-2	%	ESCA
Loss on Drying				<0.5	%	ISO787/2

<b>Heavy Metals</b>					
Lead (Pb)			Max 10	mg/kg	ICP-MS
Arsenic (As)			Max 2	mg/kg	ICP-MS
Mercury (Hg)			Max 1	mg/kg	ICP-MS
Cadmium (Cd)			Max 3	mg/kg	ICP-MS
Copper (Cu)			Max 20	mg/kg	ICP-MS
Chromium (Cr)			Max 20	mg/kg	ICP-MS
Nickel (Ni)			Max 10	mg/kg	ICP-MS
Antimony (Sb)			Max 1	mg/kg	ICP-MS

<b>Microbiological Contamination</b>	
100 cfu/g max	
Free of Pathogens in 1g	

<b>Visual And Colorimetric Evaluation</b>	Conforms	Pritty YRH
---	----------	------------

EC - Safety Data Sheet (MSDS) According to EC Directive 91/155/EEC      CLAREIUM-8004

**IMPORTANT:** The descriptions, data and information supplied above are presented in good faith and are believed to be correct and it is provided for your guidance only. Because many factors may affect processing or application and or use, we *strongly* recommend that before purchase and use of the product, that the buyer test the product in the particular intended application and or purpose under conditions expected during use to determine the suitability of the product for your particular application and or purpose. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular application and or purpose, are made regarding products described, data or information expressed. In no case shall the descriptions, information, data provided be considered a part of our terms and conditions of sale. Further, it is understood that you expressly understand and agree that the descriptions, data, and information furnished by Jiangsu Pritty Pearlescent Pigments Co., LTD and or its agents or representatives hereunder are given, without payment, and Jiangsu Pritty Pearlescent Pigments Co., LTD and or its agents or representatives assumes no obligation or liability for the description, data and information given or results obtained, all such being given and accepted at your risk. Furthermore suggestions of product applications made by Jiangsu Pritty Pearlescent Pigments Co., LTD and or its agents or representatives are our opinion only, are given without payment and with no warranty expressed or implied of the results to be obtained.

END OF TECHNICAL DATA SHEET